

GEOTEX® 200ST is a woven polypropylene geotextile containing heavy woven flat tape yarns and will meet the following Minimum Average Roll Values (MARV) when tested in accordance with the methods listed below. These characteristics make GEOTEX® 200ST ideal for the construction of embankments over soft soils, steepened slopes, and modular block and/or wrapped-face retaining walls. The geotextile is resistant to ultraviolet degradation and to biological and chemical environments normally found in soils.

GEOTEX® 200ST conforms to the property values listed below¹. Propex performs internal Manufacturing Quality Control (MQC) tests that have been accredited by the Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP). This product is NTPEP tested for AASHTO standards.

PROPERTY	TEST METHOD	MARV ²	
		ENGLISH	METRIC
MECHANICAL			
Grab Tensile Strength	ASTM D-4632	200 lbs	890 N
Grab Elongation	ASTM D-4632	15%	15%
CBR Puncture	ASTM D-6241	700 lbs	3114 N
Trapezoidal Tear	ASTM D-4533	75 lbs	334 N
ENDURANCE			
UV Resistance at 500 hrs	ASTM D-4355	70%	70%
HYDRAULIC			
Apparent Opening Size (AOS) ³	ASTM D-4751	40 US Std. Sieve	0.425 mm
Permittivity	ASTM D-4491	0.05 sec ⁻¹	0.05 sec ⁻¹
Water Flow Rate	ASTM D-4491	4 gpm/ft ²	163 l/min/m ²
ROLL SIZES ⁴		12.5 ft x 432 ft	3.81 m x 131.7 m
		15.0 ft x 360 ft	4.57 m x 109.7 m
		17.5 ft x 309 ft	5.33 m x 94.2 m

NOTES:

1. The property values listed above are effective 12/17/2018 and are subject to change without notice.
2. Values shown are in weaker principal direction. Minimum average roll values (MARV) are calculated as the typical minus two standard deviations. Statistically, it yields a 97.7% degree of confidence that any samples taken from quality assurance testing will exceed the value reported. Values represent testing at time of manufacture.
3. Maximum average roll value.
4. Contact your local Territory Business Manager (TBM) for custom widths and colors. Lead times may vary depending on customer requirements and volume requested.