

GEOTEX® 651 is a polypropylene, staple fiber, needle-punched nonwoven geotextile produced by Propex, and will meet the following Minimum Average Roll Values (MARV) when tested in accordance with the methods listed below. The fibers are needed to form a stable network that retains dimensional stability relative to each other. The geotextile is resistant to ultraviolet degradation and to biological and chemical environments normally found in soils.

GEOTEX® 651 conforms to the property values listed below¹. Propex performs internal Manufacturing Quality Control (MQC) tests that have been accredited by the Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP).

PROPERTY	TEST METHOD	MARV ²	
		ENGLISH	METRIC
ORIGIN OF MATERIALS			
% U.S. Manufactured		100%	100%
PHYSICAL			
Mass/Unit Area	ASTM D-5261	6.0 oz/yd ²	203 g/m ²
Thickness	ASTM D-5199	80 mils	2.0 mm
MECHANICAL			
Grab Tensile Strength	ASTM D-4632	170 lbs	756 N
Grab Elongation	ASTM D-4632	50%	50%
CBR Puncture	ASTM D-6241	435 lbs	1935 N
Trapezoidal Tear	ASTM D-4533	70 lbs	311 N
ENDURANCE			
UV Resistance at 500 hrs	ASTM D-4355	70%	70%
HYDRAULIC			
Apparent Opening Size (AOS) ³	ASTM D-4751	70 US Std. Sieve	0.212 mm
Permittivity	ASTM D-4491	1.5 sec ⁻¹	1.5 sec ⁻¹
Permeability	ASTM D-4491	0.38 cm/sec	0.38 cm/sec
Water Flow Rate	ASTM D-4491	110 gpm/ft ²	4482 l/min/m ²
ROLL SIZES⁴		15 ft x 300 ft	4.57 m x 91.5 m

NOTES:

- The property values listed above are effective 12/17/2018 and are subject to change without notice.
- Values shown are in weaker principal direction. Minimum average roll values (MARV) are calculated as the typical minus two standard deviations. Statistically, it yields a 97.7% degree of confidence that any samples taken from quality assurance testing will exceed the value reported. Values represent testing at time of manufacture.
- Maximum average roll value.
- Contact your local Territory Business Manager (TBM) for custom widths and colors. Lead times may vary depending on customer requirements and volume requested.