



PETROMAT[®] 4598 is a nonwoven polypropylene and recycled polyester geotextile produced by Propex, and will meet the following Minimum Average Roll Values (MARV) when tested in accordance with the methods listed below. PETROMAT 4598 is used as a moisture barrier and stress absorbing interlayer beneath asphalt overlay or a chip seal and exceeds AASHTO M288 requirements for paving fabric¹.

PETROMAT 4598 conforms to the property values listed below². Propex performs internal Manufacturing Quality Control (MQC) tests that have been accredited by the Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP). This product is NTPEP approved for AASHTO standards.

MARV³

PROPERTY	Test Method	ENGLISH	METRIC
ORIGIN OF MATERIALS			
% U.S. Manufactured		100%	100%
MATERIAL CONTENT			
Polypropylene	-	60% - 80%	60% - 80%
Recycled Polyester	-	20% - 40%	20% - 40%
PHYSICAL			
Mass/Unit Area	ASTM D-5261	4.1 oz/yd ²	139 g/m ²
Color	Visual	Gray	
MECHANICAL			
Grab Tensile Strength	ASTM D-4632	101 lbs	449 N
Grab Elongation	ASTM D-4632	50%	50%
Asphalt Retention	ASTM D-6140	0.20 gal/yd ²	0.91 l/m ²
Melting Point	ASTM D-276	320 °F	160 °C
Roll Sizes		10.5 ft x 360 ft 12.5 ft x 360 ft	10.5 ft x 360 ft 12.5 ft x 360 ft

NOTES:

1. Propex suggests that the minimum temperature of the asphalt overlay be 280 °F during installation.
2. The property values listed above are effective 12/20/2018 and are subject to change without notice. Values represent testing at time of manufacture.
3. Values shown are in weaker principal direction. Minimum average roll values (MARV) are calculated as the typical minus two standard deviations. Statistically, it yields a 97.7% degree of confidence that any samples taken from quality assurance testing will exceed the value reported.
4. Contact your local Territory Business Manager (TBM) for custom widths and colors. Lead times may vary depending on customer requirements and volume requested.



ENGINEERED PAVING SOLUTIONS[™]

www.propexglobal.com

Propex Operating Company, LLC · 4019 Industry Drive · Chattanooga, TN 37416 · ph 800 621 1273 · ph 423 855 1466

ARMORMAX[®], PYRAMAT[®], LANDLOK[®], X3[®], PYRAWALL[®], SCOURLOK[®], GEOTEX[®], PETROMAT[®], PETROTAC[®], REFLECTEX[®], and GRIDPRO[™] are registered trademarks of Propex Operating Company, LLC.

This publication should not be construed as engineering advice. While information contained in this publication is accurate to the best of our knowledge, Propex does not warrant its accuracy or completeness. The ultimate customer and user of the products should assume sole responsibility for the final determination of the suitability of the information and the products for the contemplated and actual use. The only warranty made by Propex for its products is set forth in our product data sheets for the product, or such other written warranty as may be agreed by Propex and individual customers. Propex specifically disclaims all other warranties, express or implied, including without limitation, warranties of merchantability or fitness for a particular purpose, or arising from provision of samples, a course of dealing or usage of trade.