

PETROMAT[®] Plus-White 4599W is a nonwoven polypropylene and recycled polyester geotextile produced by Propex, and will meet the following Minimum Average Roll Values (MARV) when tested in accordance with the methods listed below. PETROMAT Plus-White 4599W is used as a moisture barrier and stress absorbing interlayer beneath an asphalt overlay or a chip seal.

PETROMAT Plus-White 4599W conforms to the property values listed below². Propex performs internal Manufacturing Quality Control (MQC) tests that have been accredited by the Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP).

MARV ³			
PROPERTY	Test Method	ENGLISH	METRIC
ORIGIN OF MATERIALS			
% U.S. Manufactured		100%	100%
PHYSICAL			
Mass/Unit Area	ASTM D-5261	3.6 oz/yd ²	122 g/m ²
Color	Visual	Solar Reflective White	
MECHANICAL			
Grab Tensile Strength	ASTM D-4632	90 lbs	400 N
Grab Elongation	ASTM D-4632	50%	50%
Asphalt Retention	ASTM D-6140	0.20 gal/yd ²	0.91 l/m ²
Melting Point	ASTM D-276	320 °F	160 °C
Roll Sizes		10.5 ft x 360 ft	3.20 m x 109.7 m
		12.5 ft x 360 ft	3.81 m x 109.7 m

NOTES:

1. Propex suggests that the minimum temperature of the asphalt overlay be 280 °F during installation.
2. The property values listed above are effective 12/20/2018 and are subject to change without notice. Values represent testing at time of manufacture.
3. Values shown are in weaker principal direction. Minimum average roll values (MARV) are calculated as the typical minus two standard deviations. Statistically, it yields a 97.7% degree of confidence that any samples taken from quality assurance testing will exceed the value reported.